

Technical Data Sheet

Ricon[®] 154 DA

Powdered Dispersion of High Vinyl Butadiene

DESCRIPTION

Ricon® 154 DA is a low molecular weight, liquid polybutadiene resin, dispersed on a calcium silicate carrier for ease in handling. Ricon® 154 DA has high vinyl functionality for high reactivity, exceptional hydrophobicity and excellent processing characteristics. This resin is suitable for use in peroxide- and sulfur-cured elastomers, where it acts as a non-extractable plasticizer and process aid. Its polymeric structure gives excellent compatibility in saturated and unsaturated elastomers, especially olefinic-based elastomers and thermoplastic resins. The resin is a Type II coagent, giving excellent crosslink densities without affecting the rate of cure.

PRODUCT HIGHLIGHTS / PERFORMANCE PROPERTIES

Free flowing powder High reactivity Non-extractable process aid Electrical insulator Excellent dielectric properties Excellent hydrophobicity Low temperature flexibility Coagent for elastomer cure Good hardness Scorch protection Good compression set Abrasion resistance High tear strength

SUGGESTED APPLICATIONS

Rubber Wire and cable Sealants Thermoplastic modification

TYPICAL PHYSICAL AND CHEMICAL PROPERTIES

Property	Value	Unit
Molecular Weight (Mn)*	9,000	g/mol
1,2 Vinyl Content*	79	wt. %
Viscosity* @ 45°C	235,000	cps
Tg*	-15	°Ċ
Actives	65	%
Specific Gravity @ 25°C	1.28	-
*Resin properties		

Version Dec-24



'CRAY VALLEY' is a brand name only. The Business Unit name 'CRAY VALLEY' or the brand name 'CRAY VALLEY' may be used for promotion and/or sale of CRAY VALLEY products by TotalEnergies Petrochemicals & Refining USA Inc. ("TEPRI") or by Cray Valley SA, Cray Valley HSC Asia Limited, Cray Valley (Guangzhou) Chemical Co., Itd and Cray Valley Czech S.r.o. ("Cray Valley Legal Entities"). TEPRI and each of the Cray Valley Legal Entities are independent entities (each are individually referred to as "SELLER"). The information contained in this document is believed to be true and accurate on the date issued. Seller reserves the right to make any changes to the product according to technological progress or further developments. FINAL DETERMINATION OF SUITABILITY AND USE OF ANY PRODUCT FOR PROCESSING, USE SALE, MARKETING, OR OTHER APPLICATION(S) IS THE SOLE RESPONSIBILITY OF THE BUYER/USER. IN NO EVENT WILL ANY SELLER ASSUME ANY LIABILITY WHATSOEVER FOR THE ACCURACY OR COMPLETENESS OF THE INFORMATION CONTAINED HEREIN OR RELIANCE THERETO. SELLER MAKES NO WARRANTIES OF ANY KIND, EXPRESSED OR IMPLIED, REGARDING THE PRODUCT OR THE INFORMATION CONTAINED HEREIN OR RELIANCE THERETO. SELLER MAKES NO WARRANTIES OF ANY PARTICULAR PURPOSE, EVEN IF THAT PURPOSE IS KNOWN TO SELLER. SELLER MAKES NO REPRESENTATIONS ON WARRANTIES, EXPRESS OR IMPLED, CONCERNING OR FITNESS FOR ANY PARTICULAR PURPOSE, EVEN IF THAT PURPOSE IS NOWN TO SELLER. SELLER MAKES NO REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLED, CONCERNING OR WARRANTIES, EXPRESS OR IMPLED, OR ANY TECHNICAL SUPPORT, ANY PROPRIETARY INFORMETION, SALE, OR MARKETING, SELLER MAKES NO REPRESENTATIONS OR WARRANTIES, EXPRESS OR IMPLED, CONCERNING OR WARRANTIES, SERS OR IMPLED, OR ANY TECHNICAL SUPPORT, ANY PROPRIETARY INFORMATION PROVIDED, OR THE RESULTS THAT MIGHT BE OBTAINED FROM TECHNICAL SUPPORT. ALTERATION OF THIS DOCUMENT IS STRICLTY PROHIBITED. For further information please contact your local sales representative or visit www.crayvalley.com